

Product specification

Product name	Colour Magnet Dia13mmX6mm Pink					
Item	Name	Symbol	SI		CGS	
Shape	Diameter	D	13	mm	1.3 cm	
	Height	H	6	mm	0.6 cm	
	Direction of magnetization	M	Assiale			
	Surface treatment	Nylon	500	μ m		
Measuring point	Surface flux density	B	132.2	mT	1322 G	
	Attractive force	F	-	kgf	- gf	
	Magnetic flux density on load point	Bd	214.2	mT	2142 G	
	Total flux	Dia o	0.0000284 4	Wb	2844 Mx	
	Permeance coefficient	Pc	1.28	Pc	-	
	Operating temperature range	Tw	-	deg C	- deg F	
	Operating temperature range	Tw	-	deg C	- deg F	
Material characteristics	Material grade	Colour Magnet	Y30			
	Remanence	Br	380-420	mT	3.8-4.2 kG	
	Coercive forces	Hcb	160-216	kA/m	2.0-2.7 kOe	
	Intrinsic coercivity	Hcj	-	kA/m	- kOe	
	Maximum energy product	BH	26.3-29.5	kJ/m ³	3.3-3.7 MGOe	
	Temperature coefficient	Br	-0.18	%/deg C	31.68	%/deg F
		Hcj	-	%/deg C	-	%/deg F
	Max. operating temperature	Tw	<200	deg C	<392	deg F
	Curie temperature	Tc	460	deg C	860	deg F
	Density	P	-	kg/m ³	-	
Weight	Net	0.00398	kg	3.98	g	
Remark	REACH RoHS Directive					

Information on these magnetic characteristics are approximate and reference values. When using the calculated values for actual magnetic application products and research and development of the application of magnetic products, use these values as reference values. We are not responsible for the results from the reference values. The details can be found by referring to the product specifications. All specifications are subject to change without notice.