

# Product specification

| Product name             | Colour Magnet Star 28mmX8mm Yellow  |               |           |                   |               |
|--------------------------|-------------------------------------|---------------|-----------|-------------------|---------------|
| Item                     | Name                                | Symbol        | SI        |                   | CGS           |
| Shape                    | Diameter                            | D             | 28        | mm                | 2.8 cm        |
|                          | Height                              | H             | 8         | mm                | 0.8 cm        |
|                          | Direction of magnetization          | M             | Assiale   |                   |               |
|                          | Surface treatment                   | Nylon         | 500       | $\mu$ m           |               |
| Measuring point          | Surface flux density                | B             | 95        | mT                | 950 G         |
|                          | Attractive force                    | F             | -         | kgf               | - gf          |
|                          | Magnetic flux density on load point | Bd            | 158.1     | mT                | 1581 G        |
|                          | Total flux                          | Dia o         | 0.0000974 | Wb                | 9740 Mx       |
|                          | Permeance coefficient               | Pc            | 0.72      | Pc                | -             |
|                          | Operating temperature range         | Tw            | -         | deg C             | - deg F       |
|                          | Operating temperature range         | Tw            | -         | deg C             | - deg F       |
| Material characteristics | Material grade                      | Colour Magnet | Y30       |                   |               |
|                          | Remanence                           | Br            | 380-420   | mT                | 3.8-4.2 kG    |
|                          | Coercive forces                     | Hcb           | 160-216   | kA/m              | 2.0-2.7 kOe   |
|                          | Intrinsic coercivity                | Hcj           | -         | kA/m              | - kOe         |
|                          | Maximum energy product              | BH            | 26.3-29.5 | kJ/m <sup>3</sup> | 3.3-3.7 MGOe  |
|                          | Temperature coefficient             | Br            | -0.18     | %/deg C           | 31.68 %/deg F |
|                          |                                     | Hcj           | -         | %/deg C           | - %/deg F     |
|                          | Max. operating temperature          | Tw            | <200      | deg C             | <392 deg F    |
|                          | Curie temperature                   | Tc            | 460       | deg C             | 860 deg F     |
|                          | Density                             | P             | -         | kg/m <sup>3</sup> | -             |
| Weight                   | Net                                 | 0.0115        | kg        | 11.5 g            |               |
| Remark                   | REACH RoHS Directive                |               |           |                   |               |

Information on these magnetic characteristics are approximate and reference values. When using the calculated values for actual magnetic application products and research and development of the application of magnetic products, use these values as reference values. We are not responsible for the results from the reference values. The details can be found by referring to the product specifications. All specifications are subject to change without notice.