

# Product specification

Product name	Pot Cap Neodymium 25mmX13.5mmX5mm/M3 Countersunk S-pole					
Item	Name	Symbol	SI		CGS	
Shape	Internal diameter	ID	3.5	mm	0.35 cm	
	Subtitle	S	7	mm	0.7 cm	
	Length	L	25	mm	2.5 cm	
	Width	W	13.5	mm	1.35 cm	
	Width	w	10.3	mm	1.03 cm	
	Height	H	5	mm	0.5 cm	
	Height	h	3.4	mm	0.34 cm	
	Thickness	T	1.2	mm	0.12 cm	
	Screw	M	3	mm	0.3 cm	
	Dimensional tolerance +/-	ID		0.1	mm	0.01 cm
		L		0.1	mm	0.01 cm
		W		0.1	mm	0.01 cm
		w		0.1	mm	0.01 cm
		H		0.1	mm	0.01 cm
h			0.1	mm	0.01 cm	
	T		0.05	mm	0.005 cm	
Direction of magnetization	M	Assiale				
Surface treatment	Ni	12	$\mu$ m			
Measuring point	Surface flux density	B	-	mT	- G	
	Attractive force	F	6.23	kgf	6237 gf	
	Magnetic flux density on load point	Bd	-	mT	- G	
	Total flux	Dia o	-	Wb	- Mx	
	Permeance coefficient	Pc	-	Pc	-	
	Operating temperature range	Tw	80	deg C	176 deg F	
	Operating temperature range	Tw	-	deg C	- deg F	
Material characteristics	Material grade	Pot Cap Neodymium	35			
	Remanence	Br	1170-1220	mT	11.7-12.2 kG	
	Coercive forces	Hcb	>868	kA/m	>10.9 kOe	
	Intrinsic coercivity	Hcj	>955	kA/m	>12 kOe	
	Maximum energy product	BH	263-287	kJ/m <sup>3</sup>	33-36 MGOe	
	Temperature coefficient	Br	-0.12	%/deg C	31.78 %/deg F	
		Hcj	-0.55	%/deg C	31.01 %/deg F	
	Max. operating temperature	Tw	<80	deg C	<176 deg F	
	Curie temperature	Tc	310	deg C	590 deg F	
	Density	P	7.5	kg/m <sup>3</sup>	-	
Weight	Net	0.01128	kg	11.28 g		
Remark	REACH RoHS Directive					

Information on these magnetic characteristics are approximate and reference values. When using the calculated values for actual magnetic application products and research and development of the application of magnetic products, use these values as reference values. We are not responsible for the results from the reference values. The details can be found by referring to the product specifications. All specifications are subject to change without notice.